



COVER18 VINYL COATED POLYESTER SPECIFICATION

Style #	19290-C8	19295-C8	19297-C8	19298-C8
CONSTRUCTION	36 x 22	37 x 27	37 x 30	40 x 16
DENIER	500			
WEIGHT (ASTM D-3776)	16.1 oz/yd ²	17.0 oz/yd ²	19.5 oz/yd ²	16.9 oz/yd ²
SHADE FACTOR	90%	95%	97%	98%
THICKNESS	0.0389 in	0.0337 in	0.0359 in	0.0398 in
TENSILE STRENGTH (ASTM D-5035, Strip Method)	Warp: 313.9 lbf Fill: 188.4 lbf	Warp: 299.1 lbf Fill: 277.1 lbf	Warp: 273.3 lbf Fill: 255.0 lbf	Warp: 296.7 lbf Fill: 138.1 lbf
ELONGATION (ASTM D-5035, Strip Method)	Warp: 15.7% Fill: 11.0%	Warp: 15.7% Fill: 11.0%	Warp: 14.9% Fill: 12.5%	Warp: 18.0% Fill: 9.6%
TRAPEZOIDAL TEAR STRENGTH (ASTM D-4533)	Warp: 80.9 lbf Fill: 44.1 lbf	Warp: 82.4 lbf Fill: 51.0 lbf	Warp: 77.4 lbf Fill: 58.7 lbf	Warp: 107.6 lbf Fill: 38.3 lbf
FLAMMABILITY RATING	CA Title 19 & NFPA 701			
WEATHERABILITY (G154)	1,200 Hours			
AVAILABLE WIDTH(S)*	96", 126" (Call for current availability)			
AVAILABLE COLOR(S)*	White, White/Tan, Tan, Grey/White, Grey, Black/Grey, Black/Brown (Call for current availability)			

All "Seconds" products are available on a first come first served basis and are sold "as-is". Quality will vary from samples provided and the applicable first quality specification. Typically not more than 15% of a Seconds fabric will be considered unusable based on Buyer's discretion and knowledge of the specific application. These losses are considered normal and are an understood factor with the purchase of Seconds fabric. There is no warranty or performance guarantee whatsoever on Seconds. There are no commitments given for specific lengths of seconds fabric and <50% of rolls are typically the standard length which varies by product.