



### SCREEN1000 SPECIFICATIONS

SECONDS

Style #	19290-S1
FIBER CONTENT/FINISH	Vinyl Coated Polyester with Abrasion Resistance
CONSTRUCTION	20 x 18
DENIER	1000
WEIGHT (ASTM D-3776)	15.8 oz/yd <sup>2</sup>
SHADE FACTOR	90%
THICKNESS	0.0345 in
TENSILE STRENGTH (ASTM D-5035, Strip Method)	Warp: 269.8 lbf Fill: 225.3 lbf
ELONGATION (ASTM D-5035, Strip Method)	Warp: 29.3% Fill: 29.8%
TRAPEZOIDAL TEAR STRENGTH (ASTM D-4533)	Warp: 68.3 lbf Fill: 67.6 lbf
FLAMMABILITY RATING	CA Title 19 & NFPA 701
WEATHERABILITY (G154)	1,200 Hours
AVAILABLE WIDTH(S)*	36", 48", 60", 72", 96", 126" *Call for currently available widths.
AVAILABLE COLOR(S)*	White, Black, Tan, Grey, Brown, Tan/White, Brown/Black
<p>All "Seconds" products are available on a first come first served basis and are sold "as-is". Quality will vary from samples provided and the applicable first quality specification. Typically not more than 15% of a Seconds fabric will be considered unusable based on Buyer's discretion and knowledge of the specific application. These losses are considered normal and are an understood factor with the purchase of Seconds fabric. There is no warranty or performance guarantee whatsoever on Seconds. There are no commitments given for specific lengths of seconds fabric and &lt;50% of rolls are typically the standard length which varies by product.</p>	

\*Call for currently available widths and colors. Additional options may be available\*