



## COVER10 VINYL COATED POLYESTER SPECIFICATION

Style #	19295-C1	19297-C1	19299-C1
<b>CONSTRUCTION</b>	48 x 24	50 x 26	54 x 26
<b>DENIER</b>	220		
<b>WEIGHT</b> (ASTM D-3776)	14.1 oz/yd <sup>2</sup>	15.3 oz/yd <sup>2</sup>	16.9 oz/yd <sup>2</sup>
<b>SHADE FACTOR</b>	95%	97%	99%
<b>THICKNESS</b>	0.0281 in	0.0311 in	0.0333 in
<b>TENSILE STRENGTH</b> (ASTM D-5035, Strip Method)	Warp: 152.0 lbf Fill: 84.5 lbf	Warp: 160.7 lbf Fill: 102.6 lbf	Warp: 182.2 lbf Fill: 108.8 lbf
<b>ELONGATION</b> (ASTM D-5035, Strip Method)	Warp: 26.7% Fill: 29.4%	Warp: 20.0% Fill: 21.1%	Warp: 25.1% Fill: 23.9%
<b>TRAPEZOIDAL TEAR STRENGTH</b> (ASTM D-4533)	Warp: 25.4 lbf Fill: 9.8 lbf	Warp: 47.6 lbf Fill: 14.3 lbf	Warp: 53.1 lbf Fill: 24.2 lbf
<b>FLAMMABILITY RATING</b>	CA Title 19 & NFPA 701		
<b>WEATHERABILITY</b> (G154)	1,200 Hours		
<b>AVAILABLE WIDTH(S)*</b>	96"		
<b>AVAILABLE COLOR(S)*</b>	White, White/Tan, White/Grey, Black/White, Black/Grey, Black/Brown (Call for current availability)		

All "Seconds" products are available on a first come first served basis and are sold "as-is". Quality will vary from samples provided and the applicable first quality specification. Typically not more than 15% of a Seconds fabric will be considered unusable based on Buyer's discretion and knowledge of the specific application. These losses are considered normal and are an understood factor with the purchase of Seconds fabric. There is no warranty or performance guarantee whatsoever on Seconds. There are no commitments given for specific lengths of seconds fabric and <50% of rolls are typically the standard length which varies by product.