



**ACADIAN™**  
O U T L E T  
**DECO1000 SPECIFICATIONS**

**SECONDS**

Style #	19291-D1
<b>FIBER CONTENT/FINISH</b>	Vinyl Coated Polyester with Abrasion Resistance
<b>CONSTRUCTION</b>	37 x 11.5
<b>DENIER</b>	1000
<b>WEIGHT</b> (ASTM D-3776)	15.6 oz/yd <sup>2</sup>
<b>THICKNESS</b>	0.036 in
<b>TENSILE STRENGTH</b> (ASTM D-5035, Strip Method)	Warp: 305.3 lbf Fill: 183.5 lbf
<b>ELONGATION</b> (ASTM D-5035, Strip Method)	Warp: 13.2% Fill: 10.7%
<b>TRAPEZOIDAL TEAR STRENGTH</b> (ASTM D-4533)	Warp: 90.8 lbf Fill: 64.0 lbf
<b>WEATHERABILITY</b> (G154)	1,200 Hours
<b>AVAILABLE WIDTH(S)</b>	Call for currently available widths.
<b>AVAILABLE COLOR(S)</b>	Call for currently available colors & patterns.
<p>All "Seconds" products are available on a first come first served basis and are sold "as-is". Quality will vary from samples provided and the applicable first quality specification. Typically not more than 15% of a Seconds fabric will be considered unusable based on Buyer's discretion and knowledge of the specific application. These losses are considered normal and are an understood factor with the purchase of Seconds fabric. There is no warranty or performance guarantee whatsoever on Seconds. There are no commitments given for specific lengths of seconds fabric and &lt;50% of rolls are typically the standard length which varies by product.</p>	

\*Call for currently available widths and colors. Additional options may be available\*